

Fábrica de Papel y Oficinas en:
C/ Mayor S/N. Barrio de Villayuda
09007 Burgos
+34 947 48 32 68
+34 947 48 38 71



PAPELERAS DEL ARLANZÓN
FABRICANDO PAPEL DESDE 1865

GUARANTEED CHARACTERISTICS:

BICLASE

Standard	UNE-EN-ISO 536 g/m ² ± 3 % BASIS WEIGHT	UNE-EN-ISO 287 % ± 1,5 MOISTURE	UNE-EN-ISO 2758 Kpa -10 % BURSTING STRENGTH	ISO-9895 KN/m -10 % S.C.T.- CD
S-90	90	7,5	167	0,99
S-95	95	7,5	176	1,04
S-100	100	7,5	186	1,10
S-105	105	7,5	203	1,20
S-110	110	7,5	211	1,25
S-115	115	7,5	219	1,31
S-120	120	7,5	227	1,42
S-125	125	7,5	239	1,49
S-130	130	7,5	250	1,57
S-135	135	7,5	265	1,63
S-140	140	7,5	270	1,67
S-145	145	7,5	275	1,72
S-150	150	7,5	282	1,77
S-155	155	7,5	287	1,82
S-160	160	7,5	293	1,86
S-165	165	7,5	302	1,92
S-170	170	7,5	310	1,96
S-175	175	7,5	318	2,00